

# Review of materials and testing methods for virus filtering performance of face mask and respirator

**Bhanu Bhakta Neupane** <sup>Corresp., 1</sup>, **Basant Giri** <sup>2</sup>

<sup>1</sup> Central Department of Chemistry, Tribhuvan University, Kathmandu, Nepal

<sup>2</sup> Center for Analytical Sciences, Kathmandu Institute of Applied Sciences, Kathmandu, Nepal

Corresponding Author: Bhanu Bhakta Neupane

Email address: [bbneupane@cdctu.edu.np](mailto:bbneupane@cdctu.edu.np)

Respiratory protection device such as face mask and respirator minimize the transmission of infectious diseases by providing physical barrier to respiratory virus particles. The level of protection from a face mask and respirator depends on the nature of filter material, size of infectious particle, breathing and environmental conditions, facial seal, and user compliance. The ongoing COVID-19 pandemics has resulted in the global shortage of surgical face mask and respirator. In such situation, significant global population either have reused the single-use face mask and respirator or used a substandard face mask fabricated from locally available materials. At the same time, researchers are actively exploring filter materials having novel functionalities such as antimicrobial, enhanced charge holding, and heat regulating properties to design potentially better face mask. In this work, we reviewed research papers and guidelines published primarily in last decade focusing on, a) virus filtering efficiency, b) impact of type of filter material on filtering efficiency, c) emerging technologies in mask design, and d) decontamination approaches. Finally, we provide future prospective on the need of novel filter materials and improved design.

# **Review of materials and testing methods for virus filtering performance of face mask and respirator**

Bhanu Bhakta Neupane<sup>1\*</sup> and Basant Giri<sup>2</sup>

*1) Central Department of Chemistry, Tribhuvan University, Kathmandu, Nepal*

*2) Center for Analytical Sciences, Kathmandu Institute of Applied Sciences, Kathmandu, Nepal*

\*Correspondence: [bbneupane@cdctu.edu.np](mailto:bbneupane@cdctu.edu.np)

# Abstract

Respiratory protection device such as face mask and respirator minimize the transmission of infectious diseases by providing physical barrier to respiratory virus particles. The level of protection from a face mask and respirator depends on the nature of filter material, size of infectious particle, breathing and environmental conditions, facial seal, and user compliance. The ongoing COVID-19 pandemics has resulted in the global shortage of surgical face mask and respirator. In such situation, significant global population either have reused the single-use face mask and respirator or used a substandard face mask fabricated from locally available materials. At the same time, researchers are actively exploring filter materials having novel functionalities such as antimicrobial, enhanced charge holding, and heat regulating properties to design potentially better face mask. In this work, we reviewed research papers and guidelines published primarily in last decade focusing on: a) virus filtering efficiency, b) impact of type of filter material on filtering efficiency, c) emerging technologies in mask design, and d) decontamination approaches. Finally, we provide future prospective on the need of novel filter materials and improved design.

## 1. Introduction

We have witnessed several viral disease outbreaks in recent decades. Few notable examples of such outbreak include severe acute respiratory syndrome coronavirus-2 (SARS-CoV-2) in 2019 (Chen et al., 2020), Ebola virus in 2014 (World Health Organization, 2014), Middle East respiratory syndrome coronavirus (MERS-CoV) in 2012 (Assiri et al., 2013), influenza pandemic (H1N1) in 2009 (Yang et al., 2009) and severe acute respiratory syndrome coronavirus-1 (SARS-CoV-1) in 2002–2003 (Donnelly et al., 2003). Respiratory infection spreads through surface contact, droplet spray, and airborne modes of transmission (Atkinson & Wein, 2008; Cowling et al., 2013; Wei & Li, 2016). However, the relative contribution of each mode of transmission is not completely understood for many viruses (Janssen et al., 2013). The recent evidences have shown that COVID-19 is transmitted through contact, respiratory droplets (Huang et al., 2020; Peeri et al., 2020; World Health Organization, 2020), and aerosol routes (Greenhalgh et al., 2021). The various mode of transmission can be partly or fully interrupted by a combination of personal hygiene practices such hand washing, use of personal protective equipment (PPE) such as face mask and respirator, and physical distancing (Siegel et al., 2007).

Virus containing muco-salivary droplets ( $>5\ \mu\text{m}$ ) and aerosol particles ( $\leq 5\ \mu\text{m}$ ) are exhaled from an infected individual (both symptomatic and asymptomatic) during speaking, breathing, coughing, and sneezing activities. These particles can travel few meters in air depending on their size, gravitational settling, and evaporation rate (Yang et al., 2007a; Prather, Wang & Schooley, 2020). Face masks and respirators significantly minimize and or prevent the spread of infection by creating a physical barrier to the virus particles and droplets (Rengasamy, Zhuang & Berryann, 2004; MacIntyre & Chughtai, 2015). Particle exposure is maximum if physical distance is less than six feet and mask is not worn (Figure 1). Alternatively, maximum protection is achieved if both healthy and infected individuals properly use a recommended mask and physical distancing is maintained (World Health Organization, 2020).

**Figure 1:** A cartoon showing the importance of face mask in reducing transmission. From Ref. (Prather, Wang & Schooley, 2020). Reprinted with permission from the American Association for the Advancement of Science (AAAS).

86

## 87 **Surgical face mask**

88 A properly worn surgical mask creates a physical barrier between the immediate environment and  
 89 respiratory orifices (mouth and nose) thereby blocking or minimizing in and out movement of  
 90 infectious droplets and particles. (Seale et al., 2009) These masks are labeled as isolation, dental,  
 91 or medical procedure masks and they are generally known as facemasks. However, all facemasks  
 92 are not regulated as surgical masks. In USA, the Food and Drug Administration (FDA) regulates  
 93 surgical masks under 21 CFR 878.4040. The FDA regulation requires that the surgical mask must  
 94 have recommended filtering efficiency for inert particles and biological particles, fluid barrier  
 95 protection standards and flammability tests (see section 3) (US Food and Drug Administration,  
 96 2021). Surgical mask are designed for one time use and generally do not provide good facial seal.  
 97 The US FDA approved surgical facemasks are recommended for general public and health care  
 98 professionals at medium to low risk settings (Seale et al., 2009). Three layered flat or cup shaped  
 99 masks with stretchable ear loops or straps are the most commonly used surgical masks. Each layer  
 100 in the three-layered surgical mask is designed to have a unique functionality (figure 2a). Details  
 101 on virus filtering performance and material design of surgical mask is provided in later sections.

102 There has been a shortage of surgical masks during viral outbreaks including the ongoing  
 103 COVID-19 due to high demand in the global market (Wu et al., 2020). In such difficult situations,  
 104 general public wear homemade or locally made cloth face mask (figure 2b) and or face covering.  
 105 However, homemade masks provide limited protection to the user (Chughtai, Seale & MacIntyre,  
 106 2013; MacIntyre et al., 2015).

## 107 **Respirators and their classification**

108 Respirators are recommended for high risk environments; for example for health  
 109 professionals when providing care to COVID-19 patients (Seale et al., 2009; Phan et al., 2019;  
 110 World Health Organization, 2020). The outer rim of the respirator provides better seal or fit around  
 111 the nose and mouth. Since respirators have special design and advanced filter materials (figure 2c),  
 112 a properly worn respirator provides an expected protection to the user. Details of filtering  
 113 performance and material design of a respirator is provided in later sections.

114 A proper respirator must be selected for a specific hazards. In the USA, filtering facepiece  
 115 respirators (FFRs) (disposable half-facepiece respirators), elastomeric half- and full-facepiece

respirators, powered air-purifying respirators, supplied air respirators, self-contained breathing apparatus and combination respirators are available. The FFRs are available in N, P and R series having minimum filtering efficiency of 95 (N95, P95 and R95), 99(N99, P99 and R99) and 99.97% (N100, P100 and R100) respectively for particles having aerodynamic mass median diameter of 0.3  $\mu\text{m}$ . The letters N, P, and R refer to resistant to oil, partially resistant, and resistant (oil proof); respectively(OSHA, 1996). Other countries have different types of respirators. In UK, FFRs are available as FFP1, FFP2, and FFP3 having minimum filtering efficiency of 80%, 94% and 99.95%; respectively.

The N95 FFRs have reasonable cost and are widely used. Surgical N95 respirator are a subset of N95 FFRs which are used in healthcare settings for infectious particles. In USA, surgical N95 respirators are NIOSH certified under 42 CFR Part 84(US FDA, 1995). NIOSH reviews the results for fluid resistance, flammability, pressure difference, and biocompatibility supplied by the manufacturer for certification. The FDA also provides clearance to surgical N95 (under 21 CFR 878.4040) for fluid resistance, flammability, and biocompatibility properties. Commercial respirators come with or without exhalation valve (EV). The EV helps to minimize excessive dampness and heating and offers decreased breathing resistance. However, a faulty EV could contaminate the nearby environment with infectious virus particles thereby decreasing the level of protection. The surgical N95 respirator without EV or equivalent is recommend for MERS-CoV, SARS-CoV-1 and SARS-CoV-2 for health care professionals in high risk environments(CDC-NIOSH, 2020).

The filtering efficiency of facemask and respirator for neutral NaCl aerosol and other particles are well documented in multiple studies (Rengasamy et al., 2017; Sharma, Mishra & Mudgal, 2020; Palmieri et al., 2021) but the information on virus filtering efficiency is not well described. Also, during the COVID-19 pandemic virus filtering efficiency of facemask and respirator can be of special interest to readers. This review aims to provide in-depth details on the filter media used in face masks and respirators, their virus filtering efficiency, emerging technologies for better performing masks and respirators, and decontamination approaches. We also provide future prospective on the need of novel filter material and improved design.

## 2. Survey methodology

We used Google Scholar and PubMed platforms to search relevant documents published before February 2021. The keyword used were "facemask and virus filtering efficiency" OR "facemask and virus" OR "facemask and material". We reviewed abstract of the documents and selected documents that provided new insight on the virus filtering performance of either cloth facemask, surgical facemask, or respirators were considered further. Additionally, documents that reported significant advancement in the material design and or the understanding the facemask filter materials were also included. Patents were excluded in the study.

## 3. Filtering performance of face masks and respirators

### Filtering efficiency

A filtering device, here referring to both face mask and respirator, provides a barrier protection to the user by capturing infectious droplets, bio-aerosol, and other particles. Conventional single fiber filtration theory(Raist, 1987) predicts that the particles bigger than 0.3  $\mu\text{m}$  are captured on the filter mainly by interception and inertial impaction and particles smaller than 0.2  $\mu\text{m}$  are captured by diffusion and electrostatic attraction or polarization effects. None of the capture mechanisms are dominant for intermediate sized particles (0.2–0.3  $\mu\text{m}$ ), which are known as the most penetrating particles size (MPPS)(Hinds, 1999; Hakobyan, 2015). MPPS depends on the nature of filter material and ranges from 0.03 to 0.1  $\mu\text{m}$ (Shaffer & Rengasamy, 2009).

Filtering efficiency of a device depends on multiple parameters such as property of material used in the device, size of particle, and environmental factors. Filtering efficiency ( $E$ ) is one the most important parameters to quantify filtering performance of face mask and respirator and is given by equation 1,

$$E = \left(1 - \frac{C_i}{C_o}\right) \times 100 \quad [1]$$

where,  $C_i$  and  $C_o$  are the concentration of particles inside (downstream) and outside (upstream) the filtering device. Alternatively, the performance is also measured in terms of the penetration efficiency ( $P$ )(Johnston et al., 1992);

$$P = 100 - E = \left( \frac{C_i}{C_o} \right) \times 100 \quad [2]$$

The overall filtering performance of a respirator or class of respirators is also measured in terms of assigned protection factor (APF). APF is defined as the level of respiratory protection that a respirator or class of respirators is expected to provide to the user at the workplace when the employer implements an effective respiratory protection program on continuous basis as specified in the 29 CFR 1910.134 standard (OSHA, 2009). APF of a respirator cannot be measured simply from the known aerosol particles inside ( $C_i$ ) and outside ( $C_o$ ) the respirator. Several factors such as nature of filter media, length of exposure, facial seal, nature and concentration of contaminants, duration of exposure are considered while assigning the APF (Janssen et al., 2013). APF of 10 and 20 means a respirator reduces the exposure level by a factor of 10 and 20, respectively.

#### **In vitro measurement of filtering efficiency**

The filtering efficiency of a filtering device varies with test parameters used such as particle/aerosol size and distribution, filter media charge and particle charge, face velocity, humidity, and flow rate. For example, the filtering efficiency decreases with increase in relative humidity, face velocity, and flow rate (Yang et al., 2007b; Thakur, Das & Das, 2013). The regulatory recommendations for the use of respirator and surgical mask are made from *in vitro* measurement of filtering efficiency (NIOSH, 1996). To ensure that a device can filter even the most penetrating particles in a workplace, the filtering efficiency is measured at standard testing conditions that mimic the *worst-case scenario* in the workplace.

NIOSH uses NaCl aerosol method for testing N95 FFRs (NIOSH, 2019). The test parameters are:

- a) flow rate of 85 Lmin<sup>-1</sup> that simulates the breathing volume during a heavy work load,
- b) poly-dispersed and charge neutralized sodium chloride aerosol particles having count median diameter (CMD) of 75 ± 20 nm and geometric standard deviation (GSD) of <1.86 or broad range distribution (log-normal distribution) NaCl aerosol particles having mass median aerodynamic diameter (MMAD) and mass median diameter (MMD) about 300 nm 240 nm, respectively (Bollinger, 2004; Shaffer & Rengasamy, 2009),
- c) aerosol particle concentration of <200 mg/m<sup>3</sup>,



d) pre-conditioning of the filtering device at ~85% relative humidity and ~38° C for 24 hours.

Different test methods are used for testing the performance of material used in surgical face mask. In the ASTM F2229-03 method, surgical face mask material is challenged with charge neutralized latex spheres having size range of 0.1–5 µm at airflow test velocities (face velocity) of 0.5 to 25 cm/s (ASTM, 2003). The recommended aerosol concentration is  $10^7$ – $10^8$  particles/m<sup>3</sup> and can be diluted if needed. The US FDA recommends slightly different test parameters for testing material (not the entire mask) used in surgical face mask. This method recommends the use 0.1 µm charge un-neutralized polystyrene latex spheres at the air flow velocity of 0.5 to 25 cm/s (US Food and Drug Administration, 2004). The bacterial filtering efficiency (BFE) for the material used in surgical facemask is measured as per FDA guidance and ASTM F2101 method (ASTM, 2001). The mask material (not the whole mask) is challenged with un-neutralized *S. aureus* bacterial aerosol (mean particle size of  $3 \pm 0.3$  µm diameter) at a flow rate of 28.3 L/min. The US FDA provides clearance to surgical mask after reviewing the information provided by the manufactures in the 510(k) premarket application (US Food and Drug Administration, 2004). In the 510(k) application, the manufactures are required to provide the results of fluid resistance, polystyrene latex and *S. aureus* bacterial aerosol filtering efficiency, differential pressure, and flammability tests.

### **Virus filtering efficiency of surgical masks and respirators**

Performance of filtering device can also be measured using virus aerosol particles to calculate virus filtering efficiency (VFE). Eninger et al. (Eninger et al., 2008) measured the filtering efficiency of N95 and N99 respirators using three different virus aerosols (enterobacteriophages MS2, T4, and *Bacillus subtilis* bacteriophage) and NaCl aerosol particles at three different inhalation flow rates, 30, 80, and 150 L min<sup>-1</sup>. The filtering efficiency of both N95 and N99 respirator was ≥96% for the 0.02–0.5 µm of aerosol particles. Similar filtering efficiency was reported for virus aerosols suggesting that neutral NaCl aerosols may be appropriate for mimicking the filter penetration of similar size viruses. It is to be noted that the virus efficiency test is not required by FDA or NIOSH for approval process.

Balazy et al.(Balazy et al., 2006) measured the VFE of NIOSH certified N95 respirators and surgical masks using MS2 virus. In the study, VFE of not less than 95% was achieved using virus aerosol particles (10–80 nm) and inhalation flow rate of 85 L/min. For the test conditions, VFE of two types of surgical masks was found to be ~80% and ~ 15%, suggesting surgical masks cannot be as effective as N95 respirators for small virus.

Shimashaki et al.(Shimasaki et al., 2018) measured the penetration efficiency of two types of nonwoven fabrics [SMS type and S (Spunlace)] that are used in commercial surgical masks using  $\Phi$ X174 phase and inactivated influenza virus aerosols at a flow rate of 15 Lmin<sup>-1</sup>. The hydrodynamic diameter of the phase and influenza virus as determined by dynamic light scattering was 28 and 112 nm, respectively. The penetration efficiency for  $\Phi$ X174 phase and influenza virus was ~6% and 20% for SMS type and ~30% and 80% for S type, respectively. The three layered in SMS type may have provided lower penetration efficiency or higher efficiency. In another study, filtering efficiency of surgical N95 respirator was  $\geq 99.6\%$  for all combinations of experiment configurations using influenza A virus, rhinovirus 14, and bacteriophage  $\Phi$ X174 at a flow rate of 28.3 Lmin<sup>-1</sup>(Zhou et al., 2018).

Even though it is challenging to study the filtering efficiency of masks using *viable* virus aerosol particles, there are few studies reported. Harnish et al.(Harnish et al., 2013) measured the VFE of NIOSH approved N95 respirators using viable H1N1 virus aerosolized in artificial saliva buffer (CMD of 0.83  $\mu$ m) at a flow rates of 85 and 170 Lmin<sup>-1</sup>. The respirator was glue sealed in a six inch diameter sample holder. The N95 respirator provided VFR of 99.3% at both flow rates. They also measured the filtering efficiency using 0.8  $\mu$ m polystyrene latex beads aerosol and got similar filtering efficiency. This study suggested that the dead or live status of aerosol does not affect filtering efficiency. In another study(Harnish et al., 2016), VFE of five different models of NIOSH certified N95 respirators was measured using viable H1N1 influenza aerosol and polystyrene latex bead aerosols having CMD of 0.1  $\mu$ m representing MPPS for commonly used filter media at a flow rate of 85 Lmin<sup>-1</sup>. The mean VFE of respirators sealed to the sample holder ranged from 99.23% to 99.997% and particle aerosol filtering efficiency ranged from 99.17% to 99.995%. This study suggested that the N95 respirators can be used for protection against H1N1 virus in workplace. They also confirmed the earlier conclusion(Harnish et al., 2013) that the dead or live status of aerosol does not affect the filtering efficiency of a respirator.

## Virus filtering efficiency of cloth face masks

The particulate matter filtering performance of cloth mask have been found lower than commercially available surgical masks and respirators(Rengasamy, Eimer & Shaffer, 2010; Shakya et al., 2017; Neupane et al., 2019). Davies et al.(Davies et al., 2013) reported the filtering efficiency of two layered cloth mask made from commonly available fabrics using bacteriophage MS2 virus aerosol (~23 nm diameter) at a flow rate of 30 L min<sup>-1</sup>. The percentage filtering efficiency of cloth masks made of 100% cotton, scarf, tea towel, pillowcase, cotton mix, linen, and silk were 50.85±16.81, 48.87±19.77, 72.46±22.60, 57.13±10.55, 70.24±0.08, 61.67±2.41, 54.32±29.49, respectively. The filtering efficiency of three ply surgical mask was better (89.52±2.65%). This study suggested that homemade mask should be considered as the last option. Such masks should be worn only if no better mask is available to prevent the transmission.

A cluster randomized trial of cloth masks in healthcare workers in hospital settings reported that influenza like illness was higher in healthcare workers who wore cloth mask than those who wore surgical mask(MacIntyre & Chughtai, 2015). In a recent study(Leung et al., 2020), a significantly lower amount of coronavirus RNA in respiratory droplet and aerosols and influenza virus RNA in respiratory droplets was found in patients who wore surgical masks than in patients who did not wear surgical masks. This study suggested that surgical face masks could be used by COVID–19 patients to reduce onward transmission.

A summary of virus filtration efficiency of face masks and respirators along with few major test parameters is summarized in table 1.

## 4. Filtering efficiency and material property

An important question one can have at this point is: *what makes the filtering efficiency different?* Provided the same test parameters used, the observed difference in filtering efficiency of face masks and respirators is due to: a) inherent property of the filter material, and b) facial fitness i.e. how well the filtering device fits onto the face, and c) breathing condition.

A key component of commercially available surgical masks and respirators is a non-woven filter membrane. The membrane consists of 1–20 µm diameter fibers oriented randomly. The material can be fabricated from synthetic or natural polymers or composites such as polypropylene and

polyethylene by melt blowing technique. The membrane is mostly electrostatically charged and called as *electret filter*. The charge is imparted onto the membrane by corona discharge, induction charging, and tribo-electric techniques during fabrication(Thakur, Das & Das, 2013; Hutten, 2015). In contrast to conventional filter, electret filter provides better particle capture efficiently by electrostatic interaction. Also, the downstream air pressure drop in such filter is lower resulting in lower resistance to breathing which is referred to as better breathability(Thakur, Das & Das, 2013; Zhang et al., 2018).

The filtering efficiency of electret filter depends on charge density, charge retaining or holding capacity, and size (length and diameter) and arrangement of fiber. These parameters depend on the material type and filter manufacturing technique to a great extent. It known that filter having smaller fiber diameter leads to higher filtration efficiency than the fiber having larger diameter, but the pressure drop in the former is higher making the filtering device less breathable. In addition, shorter fiber form more porous filter than longer fiber. Filtering efficiency increases with increase in filter thickness at the expense of breathing resistance. The columbic and di-electrophoretic forces are also known to be stronger in filter having smaller fiber diameter. This results in stronger capturing of pathogens and better protection. Spun bonding and melt blowing are the most commonly adopted techniques for the fabrication of fibrous filter membrane. The melt blowing technique produces filters having smaller fiber diameter. Therefore, this is the method of choice in manufacturing of filtering media used in surgical mask and respirators(Thakur, Das & Das, 2013).

The charge density on the electret media affects the filtering performance. The charge intensity and storage capacity depends on the dielectric property of a fiber material. In general, the polymeric materials having high electrical resistance, thermal stability, and hydrophobicity (for example; polypropylene, polyethylene) provide better charge storage ability and stability(Van Turnhout, Adamse & Hoeneveld, 1980). If charge on the electret media is removed, then the filtering efficiency decreases significantly. The *most penetrating particle size* (MPPS) for electret media varies with material properties including charge density and is reported in the range of 0.03–0.1  $\mu\text{m}$ (Hinds, 1999; Shaffer & Rengasamy, 2009; Hakobyan, 2015). That is why the filtering performance of a filtering device is measured by using particles having size at or close to MPPS.

### Material design of a surgical mask

In the mostly commonly used three layered/ply SMS type surgical mask, for example US FDA approved surgical face mask, the middle layer fabricated by melt blown technique (the M layer) is sandwiched between outer and inner layers fabricated by spun bonded technique (the S layers). The three layers are designed to have specific functions. In all layers, fibers are randomly oriented (non-woven) so as to form web like arrangement (Figure 2a and inset). The fiber density in middle layer is higher than in the other two layers resulting low porosity. Since this layer is charged, it can efficiently capture infectious particles above. The outermost layer (typically coded blue) is hydrophobic and limits the penetration of water rich muco-salivary droplets. The innermost layer is hydrophilic and can absorb spit, sweat, and muco-salivary droplets thereby minimizing dampness and increasing user comfort. In recent years, surgical face mask having additional functionality are also being explored (*see* section 5).

### Material design of a cloth mask

For comparison, we also like to comment on the material property of cloth or fabric face masks. The cloth mask are made from woven or knitted fabrics and are mostly two layered. In commonly used cloth face mask, the pore size and thread density vary based on the nature of the fabrics (figure 2b and inset). The lower performance of cloth facemask (Rengasamy, Eimer & Shaffer, 2010; Shakya et al., 2017; Neupane et al., 2019; Konda et al., 2020) is also due to poor facial fitness and performance of material used. Studies have suggested to use tightly woven fabrics having high thread count and low porosity, such as quilting cotton and cotton sheets, to design relatively better performing cloth face masks (Konda et al., 2020; Neupane, Chaudhary & Sharma, 2020). The efficiency can be further increased by increasing the number of fabric layers. However, more fabric layers increase the breathing resistance making the mask uncomfortable for use (Drewnick et al., 2020; Hancock et al., 2020; Konda et al., 2020; Zangmeister et al., 2020).

**Figure 2:** Material used in a face mask and respirator. a) SMS type surgical mask and optical microscopic images of the outermost and innermost layers (the S layers) and middle layer (the M layer). (b) A typical cloth face mask and optical microscopic image of the cloth face mask surface. Reproduced with permission from Ref. (Neupane et al., 2019). c) Multilayered structure of a

respirator. Letter A and D represent the spun bonded polypropylene layers, B melt blown layer, and D support layer. The scanning electron microscopic (SEM) images layers A and D and B is also shown. Reproduced with permission from Ref. (Borkow et al., 2010).

### **Material design of a N95 respirator**

A typical NIOSH certified N95 respirator consists of four layered structure (labeled A, B, C, D in figure 2c). The outer most layer A (farthest from the face) and D (closest form the face) are made from spun bonded polypropylene(Borkow et al., 2010). These layers contain larger sized fibers and capture course particles and stop moisture entering into the inner layers. The inner layer B is made from melt blown polypropylene. It is charged (electret membrane) and contains highly packed small fibers (i.e., low porosity) and eventually can filter fine particles. The next inner layer C is made from a plain polyester and gives a shape to the respirator. This gradient filtration mechanism in the respirator provides high filtering efficiency. Another important factor for better performance of respirator is its design that provides excellent facial fit. Surgical masks are not designed to fit tightly on the face, so they cannot provide the same level of protection as the respirators(CDC-NIOSH, 2020). It is to be noted that the NIOSH certification does not look at the number of filter media layers and the order of hydrophobic and hydrophilic layers. But the N95 respirators should meet the standard test requirements as described in the 42 CFR Part 84.

## **5. Emerging technologies**

Several efforts have been reported to make better performing masks and respirators in past. Such efforts involve technologies for making new or modified filter pieces, manufacturing protocols, and disinfecting procedures among others. To contribute to the shortage of standard face mask and respirator in emergency situation, researchers, manufacturers, local hospitals, and even general public have proposed a number of innovative ideas.

### **3D printing of mask accessories**

Additive manufacturing (AM) including 3-dimensional (3D) printing have gained popularity in manufacturing medical devices (Ventola, 2014). 3D printing has been used to make mask components such as mask structure or frame, cover, filter fix, seal etc. A variety of different types of materials including polymax PLA filament, SLS/MJF nylon or flexible SLA resin have been

used. Foam or silicone band have been used to print seal with improved airtightness and softer skin touch. Even though the 3D printed masks may look like conventional PPE, they may not provide the same level of barrier protection, fluid resistance, filtration, and infection control (Ventola, 2014; Morrison et al., 2015). The new designs are not approved by any regulatory agencies yet and performance may have been compromised. Since the 3D printed masks and accessories provide low-cost, quick, and decentralized and distributed manufacturing, they can be promising during emergency situation. The US FDA has developed preliminary guidance to devices using AM that involves 3D printing (Morrison et al., 2015; Di Prima et al., 2016).

### **Modified face mask filter media**

There are several efforts to modify mask filters with various materials such as antibody and nanomaterials to enhance the antimicrobial activity and filtering efficiency of the masks. Kamiyama et al. (Kamiyama et al., 2011) reported a modified nonwoven fabric-based air filters that were impregnated with antibody for avian influenza H5N1 virus. The filters were found to inactivate the virus trapped in the filter due to antigen-antibody interaction. However, these filters were tested only for birds. All birds housed in antibody filter covered boxes did not die. Similar antibody impregnated filter could be tested for face masks. Such methods may require further research to find out how the antibody impregnated on filters would retain their activity in ambient environmental condition during transportation, storage and use of the filter. The performance of such filters while they are used in mask is not known.

Metal oxide and metal nanoparticles display biocidal activities (Vincent, Hartemann & Engels-Deutsch, 2016; Fernando, Gunasekara & Holton, 2018). In particular, copper oxide nanoparticle display potent biocidal properties against a range of microbes including bacteriophages, bronchitis virus, poliovirus, herpes simplex virus, human immunodeficiency virus and influenza viruses (Ingle, Duran & Rai, 2014; Vincent, Hartemann & Engels-Deutsch, 2016; Fernando, Gunasekara & Holton, 2018). Taking the advantage of the biocidal properties, respiratory face masks containing these materials have been tested for anti-microbial activities. The use of biocidal masks may significantly reduce the risk of hand or environmental contamination. They reduce infection due to improper handling and disposal of the masks.

A copper oxide impregnated respiratory face mask was reported by Borkow et al. (Borkow et al., 2010) that demonstrated potent anti-influenza biocidal properties without altering physical

barrier properties of the masks. The copper oxide impregnation did not alter the filtering efficiency of N95 masks when tested with aerosolized viruses of human influenza A virus (H1N1) and avian influenza virus (H9N2) under simulated breathing conditions. In these experiments, no infectious H1N1 viral titers were recovered from the copper oxide containing masks within 30 minutes. In case of H9N2 virus, titers were recovered from the copper oxide containing masks but were five-fold lower than the control masks. The copper oxide containing masks successfully passed bacterial filtration efficacy, differential pressure, latex particle challenge, and resistance to penetration (Borkow et al., 2010). The metal oxide or nanoparticle impregnated respirator could have four layers of fabric as reported by Borkow et al. (Borkow et al., 2010). Out of the four layers (Figure 2c), outer two and inner layers were metal oxide impregnated polypropylene fabric and the remaining layer was made of plain polyester to give shape to the mask.

A mixture of silver nitrate and titanium dioxide nanoparticles coated facemasks were also tested against infectious agents (Li et al., 2006). The minimum inhibitory concentration of the nanoparticles against *Escherichia coli* and *Staphylococcus aureus* were 1/128 and 1/512, respectively. A 100% reduction in viable *E. coli* and *S. aureus* was observed in the coated mask materials after 48 h of incubation. Skin irritation was not observed in any of the volunteers who wore the facemasks.

The efficacy of 4 antimicrobial respirators to decontaminate MS2 virus was evaluated (Rengasamy, Fisher & Shaffer, 2010) using MS2 as a surrogate for pathogenic viruses. The MS2 activity of masks with antimicrobial material was significantly reduced when stored at 37 °C and 80% RH for 4 hours than the masks without antimicrobial materials. The antimicrobial materials used in this research included coating of outer layer of mask with silver–copper material, incorporating EnvizO<sub>3</sub>-Shield on the outer layer of respirator, iodinated resin incorporated on filtering layer, and TiO<sub>2</sub> coated filtering layer. This study suggested that MS2 virus decontamination efficacy of antimicrobial respirators were dependent on the antimicrobial agent and storage conditions. One should note that substituting conventional filter media of facemasks with nanofiber may reduce the airflow resistance that could lead to enhanced filtration (Skaria & Smaldone, 2014).

A temperature sensitive and reusable and recyclable face mask consisting of graphene–coated nonwoven filter was recently reported by Zhong et al. (Zhong et al., 2020). This



mask provided better protection to aqueous respiratory droplets due to its super-hydrophobic surface. Additionally, the mask can be reusable by sterilizing the surface with solar illumination. Although, viruses filtering performance of the mask has not been reported, such mask might be available as next generation face mask.

#### **Virus decontamination methods**

Because of increased demand and subsequent shortage during viral outbreaks, surgical mask and respirator are decontaminated and reused. Reuse of these protective gears after proper decontamination may help fulfil supply chain constraints to some extent during the pandemics. However, improper decontamination and reuse of face masks and respirators may pose transmission risk. An ideal decontamination process is expected to inactivate any infectious material without altering the membrane integrity and filtering performance. The decontamination methods can be broadly categorized as self-deactivation and forced de-activation.

In the first approach, partly discussed in earlier section, the mask material is functionalized or additional material having novel property is incorporated so as to deactivate the pathogens. One of the strategies is to functionalize fibrous filtration unit of mask by salts such as sodium chloride (Quan et al., 2017). In this experiment, salt coating on the fiber surface dissolved when exposed to virus aerosols. The salt destroyed the pathogens when it recrystallized during drying. The salt-coated filters also showed higher filtration efficiency than conventional mask filtration layer. The virus spiked salt treated filters provided 100% survival rate of mice. Viruses captured on salt-coated filters exhibited rapid infectivity loss compared to gradual decrease on bare filters. Salt-coated filters proved highly effective in deactivating influenza viruses regardless of subtypes and following storage in harsh environmental conditions. This simple pathogen deactivation method can be helpful in obtaining a broad-spectrum, airborne pathogen prevention device in preparation for epidemic and pandemic of respiratory diseases. Similarly, a quaternary ammonium based antimicrobial surfactant was evaluated to examine its efficiency to reduce bacterial burden on FDA cleared surgical face mask surface (Tseng, Pan & Chang, 2016). The antimicrobial surfactant was covalently bound onto mask surface before use. The antimicrobial mask provided >99.3% efficiency for all three bacterial species tested. Interestingly, the antimicrobial agent on the modified mask the antimicrobial agent reduced the average colony rates by 91.8% for bioaerosols that came into contact with the mask ( $10^3$  CFU/m<sup>3</sup>). However, the rate decreased with increased bioaerosol concentrations.

In a forced de-contamination approach, pathogen is deactivated by using external agents such as vaporized hydrogen peroxide (VGP)(Kenney et al., 2020), ultraviolet germicidal irradiation (UVGI), ethylene oxide (EtO), microwave oven irradiation, autoclaving(Grinshpun, Yermakov & Khodoun, 2020), and bleach(Viscusi et al., 2009). The details of such methods are described in other reviews(Ou et al., 2020; Rodriguez-Martinez, Sossa-Briceño & Cortés-Luna, 2020). Therefore, we only briefly mention some of the selected findings.

Vaporized Hydrogen peroxide (HP) can penetrate the porous fabric that may harbor virus. The virucidal activity of HP was tested in surgical N95 respirators that were aerosolized with 3 bacteriophages: Pseudomonas phage phi-6, T7, and T1(Kenney et al., 2021). It was found that single HP vapor cycle resulted in complete eradication of the bacteriophages from the respirator.

Viscusi et al(Viscusi et al., 2009) compared the effectiveness five different decontamination methods [ethylene oxide, bleach, microwave oven irradiation, germicidal irradiation (UVGI), and vaporized hydrogen peroxide (VHP)] in nine different models of NIOSH-certified respirators (surgical N95 respirators, N95 FFRs, and P100 FFRs). Each respirator was tested for five decontamination methods and the change in odor, physical appearance, airflow resistance and aerosol penetration was studied. Also, change in material properties of the respirator and possible health risks to the user were evaluated. They found that microwave oven irradiation melted some of the samples. The scent of bleach low levels of chlorine gas were found in the decontaminated respirators. The VHP, ethylene oxide (EtO), and UVGI, were found to be better decontamination methods.

## 6. Conclusions and future perspectives

The filtering efficiency of a face mask and respirator depends on number of parameters such as nature of filter media, size of particle, and environmental parameters. The level of protection also depends on facial seal and user compliance. Several studies have shown that the N95 respirator or equivalent or higher, if worn properly, can provide expected protection to the user in high risk environments. The filtering efficiency of surgical mask is lower than the N95 respirators, and cloth face mask perform even poorer.

A few issues regarding the use of respirator and face mask are the discomfort to the user in prolonged wearing due to imperfect facial fitness, poor heat management inside the filtering

device, filter clogging, and increased breathing resistance. In worst cases, this could even lead to psychological impact(Roberge et al., 2010; Roberge, Kim & Coca, 2012) and reduced adherence and loss of workplace protection factor. So, there is need of next generation facemask and respirator having improved functionalities. The emerging 3D printing technology along with the development of novel materials such as metal organic framework (MOF)based filters (Li et al., 2019), nano-fibrous membrane containing charge enhancer(Liu et al., 2015), and use of material having high infrared transparency or reflectance for heat management during summer and winter seasons(Yang et al., 2017) will be very useful. In recent years, due to significant advancement in electrospinning technology, fabrication of filter membranes having desired fiber size, surface area, porosity, and functionality is possible. It is expected that novel facemask and respirators, which incorporate electrospun membranes, will be available commercially in future(Cheng et al., 2017; Tebyetekerwa et al., 2020; Zhang et al., 2021).

Currently used respiratory protection device pose potential risk of primary and secondary infection and transmission due to improper handling and disposing them. In viral outbreaks, because of increased demand and subsequent shortage, surgical mask and respirator are decontaminated and reused. There is still a chance of infection during decontamination process or by ineffective decontamination. Also, device interiority and performance may deteriorate, and level of protection could decrease. So, there is need for better decontamination methods other than explored in Ref(Viscusi et al., 2009; Kenney et al., 2020). Solution to this issue could be the incorporation of filter media that can self-decontaminate, partly explored in Refs.(Borkow et al., 2010; Fujimori et al., 2012; Tseng, Pan & Chang, 2016), or design of a device that could incorporate resistive heating element.

Another issue during viral outbreak, including COVID-19, is inevitable use of cloth face mask, especially in low income countries. Lower efficiency of such mask is partly due to loosen facial fitting and the material used. There is a need of low-cost and effective home-made alternative fabric material to the cloth face mask. One of the possibility for better performing cloth facemask (Zhao et al., 2020) could be the use of fabrics that can be charged electrostatically so that the filtering efficiency can be increased.

## References

- Assiri A, Al-Tawfiq JA, Al-Rabeeh AA, Al-Rabiah FA, Al-Hajjar S, Al-Barrak A, Flemman H, Al-Nassir WN, Balkhy HH, Al-Hakeem RF. 2013. Epidemiological, demographic, and clinical characteristics of 47 cases of Middle East respiratory syndrome coronavirus disease from Saudi Arabia: a descriptive study. *The Lancet infectious diseases* 13:752–761.
- ASTM. 2001. *F2101- 01: Standard test method for evaluating the bacterial filtration efficiency (BFE) of medical face mask materials, using a biological aerosol of Staphylococcus aureus. Annual Book of ASTM Standards (F2101-01): 1553-1557.*
- ASTM. 2003. *ASTM F2299-03, Standard Test Method for Determining the Initial Efficiency of Materials Used in Medical Face Masks to Penetration by Particulates Using Latex Spheres, ASTM International, West Conshohocken, PA, 2003, www.astm.org, 2003.*
- Atkinson MP, Wein LM. 2008. Quantifying the routes of transmission for pandemic influenza. *Bulletin of mathematical biology* 70:820–867.
- Balazy A, Toivola M, Adhikari A, Sivasubramani SK, Reponen T, Grinshpun SA. 2006. Do N95 respirators provide 95% protection level against airborne viruses, and how adequate are surgical masks? *American journal of infection control* 34:51–57.
- Bollinger NJ. 2004. *NIOSH respirator selection logic*. US Department of Health and Human Services, Public Health Service.
- Borkow G, Zhou SS, Page T, Gabbay J. 2010. A novel anti-influenza copper oxide containing respiratory face mask. *PLoS One* 5.
- CDC-NIOSH. 2020. Respirator Fact Sheet - Understanding Respiratory Protection Against SARS. Available at <https://www.cdc.gov/niosh/npptl/topics/respirators/factsheets/respsars.html> (accessed March 27, 2020).

- 558 Chen H, Guo J, Wang C, Luo F, Yu X, Zhang W, Li J, Zhao D, Xu D, Gong Q. 2020. Clinical characteristics  
559 and intrauterine vertical transmission potential of COVID-19 infection in nine pregnant women:  
560 a retrospective review of medical records. *The Lancet* 395:809–815.
- 561 Cheng Y, Wang C, Zhong J, Lin S, Xiao Y, Zhong Q, Jiang H, Wu N, Li W, Chen S. 2017. Electrospun  
562 polyetherimide electret nonwoven for bi-functional smart face mask. *Nano Energy* 34:562–569.
- 563 Chughtai AA, Seale H, MacIntyre CR. 2013. Use of cloth masks in the practice of infection control—  
564 evidence and policy gaps. *Int J Infect Control* 9:1–12.
- 565 Cowling BJ, Ip DK, Fang VJ, Suntarattiwong P, Olsen SJ, Levy J, Uyeki TM, Leung GM, Peiris JM,  
566 Chotpitayasunondh T. 2013. Aerosol transmission is an important mode of influenza A virus  
567 spread. *Nature communications* 4:1935.
- 568 Davies A, Thompson K-A, Giri K, Kafatos G, Walker J, Bennett A. 2013. Testing the efficacy of homemade  
569 masks: would they protect in an influenza pandemic? *Disaster medicine and public health*  
570 *preparedness* 7:413–418.
- 571 Di Prima M, Coburn J, Hwang D, Kelly J, Khairuzzaman A, Ricles L. 2016. Additively manufactured medical  
572 products—the FDA perspective. *3D printing in medicine* 2:1–6.
- 573 Donnelly CA, Ghani AC, Leung GM, Hedley AJ, Fraser C, Riley S, Abu-Raddad LJ, Ho L-M, Thach T-Q, Chau  
574 P. 2003. Epidemiological determinants of spread of causal agent of severe acute respiratory  
575 syndrome in Hong Kong. *The Lancet* 361:1761–1766.
- 576 Drewnick F, Pikmann J, Fachinger F, Moormann L, Sprang F, Borrmann S. 2020. Aerosol filtration  
577 efficiency of household materials for homemade face masks: Influence of material properties,  
578 particle size, particle electrical charge, face velocity, and leaks. *Aerosol Science and*  
579 *Technology*:1–17.

- Eninger RM, Honda T, Adhikari A, Heinonen-Tanski H, Reponen T, Grinshpun SA. 2008. Filter performance of N99 and N95 facepiece respirators against viruses and ultrafine particles. *Annals of occupational hygiene* 52:385–396.
- Fernando SSN, Gunasekara T, Holton J. 2018. Antimicrobial Nanoparticles: applications and mechanisms of action.
- Fujimori Y, Sato T, Hayata T, Nagao T, Nakayama M, Nakayama T, Sugamata R, Suzuki K. 2012. Novel antiviral characteristics of nanosized copper (I) iodide particles showing inactivation activity against 2009 pandemic H1N1 influenza virus. *Appl. Environ. Microbiol.* 78:951–955.
- Greenhalgh T, Jimenez JL, Prather KA, Tufekci Z, Fisman D, Schooley R. 2021. Ten scientific reasons in support of airborne transmission of SARS-CoV-2. *The lancet* 397:1603–1605.
- Grinshpun SA, Yermakov M, Khodoun M. 2020. Autoclave sterilization and ethanol treatment of re-used surgical masks and N95 respirators during COVID-19: impact on their performance and integrity. *Journal of Hospital Infection* 105:608–614.
- Hakobyan NA. 2015. Introduction to basics of submicron aerosol particles filtration theory via ultrafine fiber media. *Armenian Journal of Physics* 8:140–151.
- Hancock JN, Plumley MJ, Schilling K, Sheets D, Wilen L. 2020. Comment on “Aerosol Filtration Efficiency of Common Fabrics Used in Respiratory Cloth Masks.” *ACS nano* 14:10758–10763.
- Harnish DA, Heimbuch BK, Balzli C, Choe M, Lumley AE, Shaffer RE, Wander JD. 2016. Capture of 0.1- $\mu$ m aerosol particles containing viable H1N1 influenza virus by N95 filtering facepiece respirators. *Journal of occupational and environmental hygiene* 13:D46–D49.
- Harnish DA, Heimbuch BK, Husband M, Lumley AE, Kinney K, Shaffer RE, Wander JD. 2013. Challenge of N95 filtering facepiece respirators with viable H1N1 influenza aerosols. *Infection Control & Hospital Epidemiology* 34:494–499.

- 603 Hinds WC. 1999. Properties, behavior, and measurement of airborne particles. *Aerosol Technology, 2nd*  
604 *ed. John Wiley and Sons Press, New York:182–204.*
- 605 Huang C, Wang Y, Li X, Ren L, Zhao J, Hu Y, Zhang L, Fan G, Xu J, Gu X. 2020. Clinical features of patients  
606 infected with 2019 novel coronavirus in Wuhan, China. *The Lancet* 395:497–506.
- 607 Hutten IM. 2015. *Handbook of nonwoven filter media*. Butterworth-Heinemann.
- 608 Ingle AP, Duran N, Rai M. 2014. Bioactivity, mechanism of action, and cytotoxicity of copper-based  
609 nanoparticles: a review. *Applied microbiology and biotechnology* 98:1001–1009.
- 610 Janssen L, Ettinger H, Graham S, Shaffer R, Zhuang Z. 2013. Commentary: the use of respirators to  
611 reduce inhalation of airborne biological agents. *Journal of occupational and environmental*  
612 *hygiene* 10:D97–D103.
- 613 Johnston AR, Myers WR, Colton CE, Birkner JS, Campbell CE. 1992. Review of respirator performance  
614 testing in the workplace: issues and concerns. *American Industrial Hygiene Association Journal*  
615 53:705–712.
- 616 Kamiyama Y, Adachi K, Handharyani E, Soejoedono RD, Kusano T, Inai M, Tsukamoto M, Kashiwagi S,  
617 Tsukamoto Y. 2011. Protection from avian influenza H5N1 virus infection with antibody-  
618 impregnated filters. *Virology journal* 8:54.
- 619 Kenney P, Chan BK, Kortright K, Cintron M, Havill N, Russi M, Epright J, Lee L, Balcezak T, Martinello R.  
620 2020. Hydrogen Peroxide Vapor sterilization of N95 respirators for reuse. *medRxiv*.
- 621 Kenney PA, Chan BK, Kortright KE, Cintron M, Russi M, Epright J, Lee L, Balcezak TJ, Havill NL, Martinello  
622 RA. 2021. Hydrogen peroxide vapor decontamination of N95 respirators for reuse. *Infection*  
623 *Control & Hospital Epidemiology:1–14.*
- 624 Konda A, Prakash A, Moss GA, Schmoldt M, Grant GD, Guha S. 2020. Aerosol Filtration Efficiency of  
625 Common Fabrics Used in Respiratory Cloth Masks. *ACS Nano* 14:6339–6347.

- 626 Leung NH, Chu DK, Shiu EY, Chan K-H, McDevitt JJ, Hau BJ, Yen H-L, Li Y, KM D, Ip JS. 2020. Respiratory  
627 Virus Shedding in Exhaled Breath and Efficacy of Face Masks. *Nature methods*. DOI:  
628 <https://doi.org/10.1038/s41591-020-0843-2>.
- 629 Li Y, Leung P, Yao L, Song QW, Newton E. 2006. Antimicrobial effect of surgical masks coated with  
630 nanoparticles. *Journal of Hospital Infection* 62:58–63.
- 631 Li P, Li J, Feng X, Li J, Hao Y, Zhang J, Wang H, Yin A, Zhou J, Ma X. 2019. Metal-organic frameworks with  
632 photocatalytic bactericidal activity for integrated air cleaning. *Nature communications* 10:1–10.
- 633 Liu C, Hsu P-C, Lee H-W, Ye M, Zheng G, Liu N, Li W, Cui Y. 2015. Transparent air filter for high-efficiency  
634 PM 2.5 capture. *Nature communications* 6:1–9.
- 635 MacIntyre CR, Chughtai AA. 2015. Facemasks for the prevention of infection in healthcare and  
636 community settings. *Bmj* 350:h694.
- 637 MacIntyre CR, Seale H, Dung TC, Hien NT, Nga PT, Chughtai AA, Rahman B, Dwyer DE, Wang Q. 2015. A  
638 cluster randomised trial of cloth masks compared with medical masks in healthcare workers.  
639 *BMJ open* 5:e006577.
- 640 Morrison RJ, Kashlan KN, Flanagan CL, Wright JK, Green GE, Hollister SJ, Weatherwax KJ. 2015.  
641 Regulatory considerations in the design and manufacturing of implantable 3D-printed medical  
642 devices. *Clinical and translational science* 8:594–600.
- 643 Neupane BB, Chaudhary RK, Sharma A. 2020. A smartphone microscopic method for rapid screening of  
644 cloth facemask fabrics during pandemics. *PeerJ* 8:e9647.
- 645 Neupane BB, Mainali S, Sharma A, Giri B. 2019. Optical microscopic study of surface morphology and  
646 filtering efficiency of face masks. *PeerJ* 7:e7142.
- 647 NIOSH. 1996. Guide to the selection and use of particulate respirators certified under 42 CFR 84. DOI:  
648 10.26616/NIOSH PUB96101.



- 649 NIOSH. 2019. Procedure No. TEB-APR-STP-0059, Revision 2.0. Determination of particulate filter  
650 efficiency level for N95 series filters against solid particulates for non-powered, airpurifying  
651 respirators standard testing procedure (STP). Available at [http://www.](http://www.cdc.gov/niosh/nppt/stps/pdfs/TEB-APR-STP-0059.pdf)  
652 [cdc.gov/niosh/nppt/stps/pdfs/TEB-APR-STP-0059.pdf](http://www.cdc.gov/niosh/nppt/stps/pdfs/TEB-APR-STP-0059.pdf). (accessed July 22, 2021).
- 653 OSHA. 1996. Particulate Respirators Certified under 42 CFR Part 84. Available at  
654 <https://www.osha.gov/laws-regs/standardinterpretations/1996-09-03> (accessed August 15,  
655 2021).
- 656 OSHA. 2009. *Assigned protection factor for revised respiratory protection standard*.
- 657 Ou Q, Pei C, Kim SC, Abell E, Pui DY. 2020. Evaluation of decontamination methods for commercial and  
658 alternative respirator and mask materials—view from filtration aspect. *Journal of Aerosol Science*  
659 150:105609.
- 660 Palmieri V, De Maio F, De Spirito M, Papi M. 2021. Face masks and nanotechnology: Keep the blue side  
661 up. *Nano Today* 37:101077.
- 662 Peeri NC, Shrestha N, Rahman MS, Zaki R, Tan Z, Bibi S, Baghbanzadeh M, Aghamohammadi N, Zhang W,  
663 Haque U. 2020. The SARS, MERS and novel coronavirus (COVID-19) epidemics, the newest and  
664 biggest global health threats: what lessons have we learned? *International journal of*  
665 *epidemiology*.
- 666 Phan LT, Sweeney D, Maita D, Moritz DC, Bleasdale SC, Jones RM, Program CPE. 2019. Respiratory  
667 viruses on personal protective equipment and bodies of healthcare workers. *Infection Control &*  
668 *Hospital Epidemiology* 40:1356–1360.
- 669 Prather KA, Wang CC, Schooley RT. 2020. Reducing transmission of SARS-CoV-2. *Science* 368:1422–1424.
- 670 Quan F-S, Rubino I, Lee S-H, Koch B, Choi H-J. 2017. Universal and reusable virus deactivation system for  
671 respiratory protection. *Scientific reports* 7:1–10.
- 672 Raist P. 1987. *Aerosols. Introduction to the Theory*. Mir, Moscow.

- 673 Rengasamy S, Eimer B, Shaffer RE. 2010. Simple respiratory protection—evaluation of the filtration  
674 performance of cloth masks and common fabric materials against 20–1000 nm size particles.  
675 *Annals of occupational hygiene* 54:789–798.
- 676 Rengasamy S, Fisher E, Shaffer RE. 2010. Evaluation of the survivability of MS2 viral aerosols deposited  
677 on filtering face piece respirator samples incorporating antimicrobial technologies. *American*  
678 *journal of infection control* 38:9–17.
- 679 Rengasamy S, Shaffer R, Williams B, Smit S. 2017. A comparison of facemask and respirator filtration test  
680 methods. *Journal of occupational and environmental hygiene* 14:92–103.
- 681 Rengasamy A, Zhuang Z, Berryann R. 2004. Respiratory protection against bioaerosols: literature review  
682 and research needs. *American Journal of Infection Control* 32:345–354. DOI:  
683 10.1016/j.ajic.2004.04.199.
- 684 Roberge RJ, Coca A, Williams WJ, Powell JB, Palmiero AJ. 2010. Physiological impact of the N95 filtering  
685 facepiece respirator on healthcare workers. *Respiratory care* 55:569–577.
- 686 Roberge RJ, Kim J-H, Coca A. 2012. Protective facemask impact on human thermoregulation: an  
687 overview. *Annals of occupational hygiene* 56:102–112.
- 688 Rodriguez-Martinez CE, Sossa-Briceño MP, Cortés-Luna JA. 2020. Decontamination and reuse of N95  
689 filtering facemask respirators: a systematic review of the literature. *American journal of*  
690 *infection control* 48:1520–1532.
- 691 Seale H, Dwyer DE, Cowling BJ, Wang Q, Yang P, MacIntyre CR. 2009. A review of medical masks and  
692 respirators for use during an influenza pandemic. *Influenza and other respiratory viruses* 3:205.
- 693 Shaffer RE, Rengasamy S. 2009. Respiratory protection against airborne nanoparticles: a review. *Journal*  
694 *of nanoparticle research* 11:1661.

- 695 Shakya KM, Noyes A, Kallin R, Peltier RE. 2017. Evaluating the efficacy of cloth facemasks in reducing  
696 particulate matter exposure. *Journal of Exposure Science & Environmental Epidemiology* 27:352–  
697 357. DOI: 10.1038/jes.2016.42.
- 698 Sharma SK, Mishra M, Mudgal SK. 2020. Efficacy of cloth face mask in prevention of novel coronavirus  
699 infection transmission: A systematic review and meta-analysis. *Journal of education and health*  
700 *promotion* 9:192.
- 701 Shimasaki N, Okaue A, Kikuno R, Shinohara K. 2018. Comparison of the Filter Efficiency of Medical  
702 Nonwoven Fabrics against Three Different Microbe Aerosols. *Biocontrol science* 23:61–69.
- 703 Siegel JD, Rhinehart E, Jackson M, Chiarello L. 2007. 2007 Guideline for isolation precautions preventing  
704 transmission of infectious agents in healthcare settings.
- 705 Skaria SD, Smaldone GC. 2014. Respiratory source control using surgical masks with nanofiber media.  
706 *Annals of occupational hygiene* 58:771–781.
- 707 Tebyetekerwa M, Xu Z, Yang S, Ramakrishna S. 2020. Electrospun nanofibers-based face masks.  
708 *Advanced Fiber Materials* 2:161–166.
- 709 Thakur R, Das D, Das A. 2013. Electret air filters. *Separation & Purification Reviews* 42:87–129.
- 710 Tseng C-C, Pan Z-M, Chang C-H. 2016. Application of a quaternary ammonium agent on surgical face  
711 masks before use for pre-decontamination of nosocomial infection-related bioaerosols. *Aerosol*  
712 *Science and Technology* 50:199–210.
- 713 US FDA. 1995. 42 Code of Federal Regulations Part 84. Respiratory Protective Devices. Final Rules and  
714 Notice. U.S. Government Printing Office, Office of Federal Register, Washington, D.C. 60: 30335-  
715 30398 (1995).
- 716 US Food and Drug Administration. 2004. Guidance for industry and FDA staff. Surgical masks -premarket  
717 notification [510(k)] submissions; Guidance for industry and FDA. Available at


- 718 [https://www.fda.gov/regulatory-information/search-fda-guidance-documents/surgical-masks-](https://www.fda.gov/regulatory-information/search-fda-guidance-documents/surgical-masks-premarket-notification-510k-submissions)
- 719 [premarket-notification-510k-submissions](https://www.fda.gov/regulatory-information/search-fda-guidance-documents/surgical-masks-premarket-notification-510k-submissions) (accessed July 21, 2021).
- 720 US Food and Drug Administration. 2021. N95 Respirators, Surgical Masks, and Face Masks. Available at
- 721 [https://www.fda.gov/medical-devices/personal-protective-equipment-infection-control/n95-](https://www.fda.gov/medical-devices/personal-protective-equipment-infection-control/n95-respirators-surgical-masks-and-face-masks)
- 722 [respirators-surgical-masks-and-face-masks](https://www.fda.gov/medical-devices/personal-protective-equipment-infection-control/n95-respirators-surgical-masks-and-face-masks) (accessed July 20, 2021).
- 723 Van Turnhout J, Adamse JWC, Hoeneveld WJ. 1980. Electret filters for high-efficiency air cleaning.
- 724 *Journal of Electrostatics* 8:369–379.
- 725 Ventola CL. 2014. Medical applications for 3D printing: current and projected uses. *Pharmacy and*
- 726 *Therapeutics* 39:704.
- 727 Vincent M, Hartemann P, Engels-Deutsch M. 2016. Antimicrobial applications of copper. *International*
- 728 *journal of hygiene and environmental health* 219:585–591.
- 729 Viscusi DJ, Bergman MS, Eimer BC, Shaffer RE. 2009. Evaluation of five decontamination methods for
- 730 filtering facepiece respirators. *Annals of occupational hygiene* 53:815–827.
- 731 Wei J, Li Y. 2016. Airborne spread of infectious agents in the indoor environment. *American Journal of*
- 732 *Infection Control* 44:S102–S108.
- 733 World Health Organization. 2014. *Interim infection prevention and control guidance for care of patients*
- 734 *with suspected or confirmed filovirus haemorrhagic fever in health-care settings, with focus on*
- 735 *Ebola*. World Health Organization.
- 736 World Health Organization. 2020. The COVID-19 risk communication package for healthcare facilities.
- 737 Wu H, Huang J, Zhang CJ, He Z, Ming W-K. 2020. Facemask shortage and the novel coronavirus disease
- 738 (COVID-19) outbreak: Reflections on public health measures. *EClinicalMedicine*:100329.
- 739 Yang A, Cai L, Zhang R, Wang J, Hsu P-C, Wang H, Zhou G, Xu J, Cui Y. 2017. Thermal management in
- 740 nanofiber-based face mask. *Nano Letters* 17:3506–3510.

- 741 Yang S, Lee GW, Chen C-M, Wu C-C, Yu K-P. 2007a. The size and concentration of droplets generated by  
742 coughing in human subjects. *Journal of Aerosol Medicine* 20:484–494.
- 743 Yang S, Lee W-MG, Huang H-L, Huang Y-C, Luo C-H, Wu C-C, Yu K-P. 2007b. Aerosol penetration  
744 properties of an electret filter with submicron aerosols with various operating factors. *Journal of*  
745 *Environmental Science and Health Part A* 42:51–57.
- 746 Yang Y, Sugimoto JD, Halloran ME, Basta NE, Chao DL, Matrajt L, Potter G, Kenah E, Longini IM. 2009.  
747 The transmissibility and control of pandemic influenza A (H1N1) virus. *Science* 326:729–733.
- 748 Zangmeister CD, Radney JG, Vicenzi EP, Weaver JL. 2020. Filtration efficiencies of nanoscale aerosol by  
749 cloth mask materials used to slow the spread of SARS-CoV-2. *ACS nano* 14:9188–9200.
- 750 Zhang Z, Ji D, He H, Ramakrishna S. 2021. Electrospun ultrafine fibers for advanced face masks. *Materials*  
751 *Science and Engineering: R: Reports* 143:100594.
- 752 Zhang H, Liu J, Zhang X, Huang C, Jin X. 2018. Design of electret polypropylene melt blown air filtration  
753 material containing nucleating agent for effective PM2. 5 capture. *RSC advances* 8:7932–7941.
- 754 Zhao M, Liao L, Xiao W, Yu X, Wang H, Wang Q, Lin YL, Kilinc-Balci FS, Price A, Chu L, Mary C C, Chu S, Yi  
755 C. 2020. Household materials selection for homemade cloth face coverings and their filtration  
756 efficiency enhancement with triboelectric charging. *Nano Letters* 20:5544–5552.
- 757 Zhong H, Zhu Z, Lin J, Cheung CF, Lu VL, Yan F, Chan C-Y, Li G. 2020. Reusable and recyclable graphene  
758 masks with outstanding superhydrophobic and photothermal performances. *ACS nano* 14:6213–  
759 6221.
- 760 Zhou SS, Lukula S, Chiossone C, Nims RW, Suchmann DB, Ijaz MK. 2018. Assessment of a respiratory face  
761 mask for capturing air pollutants and pathogens including human influenza and rhinoviruses.  
762 *Journal of thoracic disease* 10:2059.
- 763

# Figure 1

A cartoon showing the importance of face mask in reducing transmission.


Reproduced with permission from Ref. (Prather, Wang & Schooley, 2020) . Copyright © 2020, American Association for the Advancement of Science.



## Figure 2

### Material used in face mask and respirator

a) SMS type surgical mask and optical microscopic images of the outermost and innermost layers (the S layers) and middle layer (the M layer). (b) A typical cloth face mask and optical microscopic image of the cloth face mask surface. Reproduced with permission from Ref. (Neupane et al., 2019) . c) Multilayered structure of a respirator. Letter A and D represent the spun bonded polypropylene layers, B melt blown layer, and D support layer. The scanning electron microscopic (SEM) images layers A and D and B is also shown. Reproduced with permission from Ref. (Borkow et al., 2010) .





## Table 1 (on next page)

Filtering efficiency

A comparison of virus filtration efficiencies.

**Table 1:** Comparison of virus filtration efficiencies

Filtering device	Filtration efficiency	Major test parameters
<b>N95</b>	$\geq 95\%$	MS2 virus aerosol, flow rate $85 \text{ L min}^{-1}$ (Balazy et al., 2006)
	$\geq 99.2\%$	H1N1 viable virus, flow rate $85 \text{ L min}^{-1}$ (Harnish et al., 2016)
	97.1-97.8%	bacteriophage phiX174, $28.3 \text{ L min}^{-1}$ (Rengasamy et al., 2017)
<b>Three layered surgical mask</b>	$\sim 85\%$	MS2 virus aerosol, flow rate $85 \text{ L min}^{-1}$ (Balazy et al., 2006)
	$\sim 94\%$	bacteriophage <i>phiX174</i> , flow rate $15 \text{ L min}^{-1}$ (Shimasaki et al., 2018)
	$\sim 80\%$	Influenza virus, flow rate $15 \text{ L min}^{-1}$ (Shimasaki et al., 2018)
	$\sim 90\%$	bacteriophage MS2, flow rate $30 \text{ L min}^{-1}$
<b>Two layered cloth mask</b>	50-70%	bacteriophage MS2, flow rate $30 \text{ L min}^{-1}$